

CLASSIC PEARL WHITE 33MIC BOPP THERMAL FILM

AVAILABLE:33MIC

www.kangdixin.com

KDX

II PRODUCT DESCRIPTION

It is a BOPP substrated product with perlite surface. The special finish creates a luxurious appearance to attract the buyers' attention and increase the perceived value of the product. The product is non-toxic and environmentally friendly, low level of static, consistent corona treatment, excellent resistance to tear & elongation, primarily used in the printing industry.

II FEATURES

- Excellent perlite finish look
- Excellent resistance to tear & elongation

II TECHNICAL DATA

PROPERTIES		TEST METHOD
Thickness, μm	33	GB/T6672
Perlite Film Thickness, μm	25	GB/T6672
Adhesive thickness, μm	8	GB/T6672
Yield, m^2/kg	41.3	
Wetting Tension, mN/m		
Perlite surface:	≥ 40	GB/T14216
Adhesive surface:	≥ 36	
Haze, %	≥ 70	ASTM D1003
C.O.F. out/out	≤ 0.5	ASTM D1894
Heat Shrinkage(120 $^{\circ}\text{C}$ 30s), %		
MD	≤ 2.0	Q/CPKDX0001
TD	≤ 1.0	

II APPLICATION TECHNOLOGY

Adjust the processing parameter according to the production job requirement.

Laminating Equipment : thermal laminating machine

Temperature : 95-120 $^{\circ}\text{C}$

Pressure : 8-18mpa

Speed : 10-70m/min

For further information and details,
please contact your local KDX
organization.

KDX CHINA

No.26 Zhenxing Road,
Changping Dist. Beijing,
China 102200
sales@kdxfilm.com
www.kangdexin.com

KDX EUROPE

Klarenanstelerweg 6,
6468 EP Kerkrade,
The Netherlands
info@kdx europe.com
www.kdx europe.com

KDX AMERICA

8880 Mistletoe Dr. Easton, MD 21601
sales@kdxamerica.com
www.kdxamerica.com