



Technology Refines Life

# Ceramic Series

A New Generation of High Performance  
Ceramic Window Film

Excellent Performance and Metal-free Properties



Metal free, no signal  
interference



Superior Heat Rejection



Low Reflection



Custom thickness  
(2mil/4mil)



High Clarity



Quick Drying \*



\* Support customized quick-drying version

# Automotive Window Film

	T75	T80	T15	T30	CM15	CM25	CM35
VLT(%)	75	83	13	31	12	25	36
VLR(Ext) (%)	9	10	5	5	6	6	7
VLR(Int) (%)	9	10	6	6	6	6	6
UVR(%)	≥99	≥99	≥99	≥99	≥99	≥99	≥99
IRR(%) (900-1000nm)	88	61	90	87	86	86	—
TSER(%)	44	28	65	57	64	59	55
Thickness (mil)	2.0/4.0	2.0/4.0	2.0/4.0	2.0/4.0	2.0	2.0	2.0

**Note:** Published values are generated from films tested on 1/8" (3mm) thick clear glass. All data values above are representative and are provided for comparison purposes only.

## KDX CHINA

No.26 Zhenxing Road, Changping Dist.  
Beijing, China 102200  
sales@kdxfilm.com  
Tel: +86-010-82282777  
www.kdxwindowfilm.com

## KDX EUROPE

Klarenanstelerweg 6,  
6468 EP Kerkrade, The Netherlands  
info@kdx europe.com  
Tel: +31 (0) 45 546 6100  
www.kdxwindowfilm.com

## KDX AMERICA

8880 Mistletoe Dr. Easton, MD 21601  
sales@kdxamerica.com  
Tel: 1-877-492-9210 (Toll Free)  
www.kdxwindowfilm.com