



**PREMIUM METALIZED
SILVER 25MIC PET
THERMAL FILM**

www.kangdexin.com.cn

KDX

II PRODUCT DESCRIPTION

It is a BOPET based product with Silver metallic luster. The product is non-toxic and environmentally friendly, low level of static, consistent corona treatment, excellent resistance to tear & elongation, primarily used in the printing industry. The film accepts UV spot varnishing, foil stamping as well as screen printing.

II FEATURES

- Excellent printability
- Excellent silver metallic luster
- Excellent resistance to tear & elongation

II TECHNICAL DATA

PROPERTIES	TYPICAL VALUE	TEST METHOD
Thickness, μm	25	GB/T6672
Yield, m^2/kg	36.1	
Wetting Tension, mN/m		
BOPET surface:	≥ 38	GB/T14216
Adhesive surface:	≥ 48	
Heat Shrinkage, %		
MD	≤ 2.0	Q/CPKDX0001
TD	≥ 1.0	
Coefficient of Friction		
Outside / Outside	≤ 0.5	ASTM D1894

II APPLICATION TECHNOLOGY

Adjust the processing parameter according to the production job requirement.

Laminating Equipment : thermal laminating machine

Temperature : 95-120 $^{\circ}\text{C}$ Pressure : 8-18MPa Speed : 10-70m/min

II STORAGE AND HANDLING

- Keep upright in a clean, dry and ventilated warehouse ($T=5-30^{\circ}\text{C}$, $H=20-60\%$); avoid storage in direct sunlight or near sources of heat less than 2m.
- In order to avoid damage to the film surface or end surface, avoid collision during product transportation, loading and unloading process.
- When using a thermal laminating film in winter, it should be placed in the production room in advance so that the temperature of the film is higher

II SHELF LIFE

12 months.

For further information and details, please contact your local KDX organization.

KDX CHINA

No.26 Zhenxing Road,
Chanping Dist. Beijing,
China 102200
sales@kdxfilm.com
www.kangdexin.com

KDX EUROPE

Klarenansterweg 6,
6468 EP Kerkrade,
The Netherlands
info@kdx europe.com
www.kdx europe.com

KDX AMERICA

8880 Mistletoe Dr. Easton, MD 21601
sales@kdxamerica.com
www.kdxamerica.com